

TUBING ACERO INOXIDABLE AUSTENTICO EN LIBRAS POR FT.

ANEXO # 4

Tubing O.D. (Inches)		Wall Thickness (Gauges & Inches)					
		25	22	20	18	16	14
		.020	.028	.035	.049	.065	.083
1/8	.125	.0226	.0293	.0339	—————	—————	—————
3/16	.188	.0362	.0482	.0577	.0734	.0862	—————
1/4	.250	.0496	.0670	.0812	.1062	.1296	.1494
5/16	.313	.0632	.0860	.1049	.1395	.1738	.2058
3/8	.375	.0765	.1048	.1283	.1722	.2172	.2613
1/2	.500	.1035	.1424	.1754	.2382	.3048	.3731
5/8	.625	.1304	.1802	.2226	.3043	.3924	.4849
3/4	.750	.1574	.2179	.2698	.3703	.4800	.5968
7/8	.875	.1843	.2557	.3169	.4363	.5676	.7086
1	1.000	.2113	.2934	.3641	.5023	.6552	.8205
1 1/8	1.125	.2382	.3311	.4112	.5683	.7427	.9323
1 1/4	1.250	.2652	.3688	.4584	.6344	.8303	1.0442
1 3/8	1.375	.2921	.4066	.5056	.7004	.9179	1.1560
1 1/2	1.500	.3191	.4443	.5527	.7664	1.0055	1.2678

Factor (.4536) para Calcular de Libras a Kilos
 Longitud Standard 20'Ft. (6.10 mts.)